

Test Report

Report No.: CTT2409010211EN

Page 1 of 3

Applicant: Ruier Brand Management Co., LTD

Address: Room 204, No.5, Hualian 2nd Road, Pengxi Lianbian, Helong Street, Baiyun District, Guangzhou City, China

Sample Received Date: Sep. 02, 2024

Completed Date: Sep. 06, 2024

Report Date: Sep. 06, 2024

The following merchandise was (were) submitted and identified on behalf of the applicant as:

Sample Name: Sleemon Leather

Model No.: 058350

Other Information: WK-519PCM OK-652PCF OY-1644MJF WK-667PCM WK-672PCM

Test Result(s): Please refer to next page(s).

Test Requested and Conclusion(s):

No.	Standard and Requirement	Conclusion(s)
1	Annex XVII items 72 of the REACH Regulation (EC) No 1907/2006 - Extractable Heavy Metals	PASS
2	Annex XVII items 72 of the REACH Regulation (EC) No 1907/2006 - Polycyclic aromatic hydrocarbons	PASS

Signed for and on Behalf of CTT:



Tony Ye
Technical Manager



Verification Report

Test Report

Report No.: CTT2409010211EN

Page 2 of 3

Test Result(s):

Extractable Heavy Metals - Annex XVII items 72 of the REACH Regulation (EC) No 1907/2006

Method: EN 16711-2:2015, analyzed by Inductively coupled plasma mass spectrometry (ICP-MS) or Inductively Coupled Plasma Optical Emission Spectrometer (ICP-OES) .

Substances	Arsenic (As)	Cadmium (Cd)	Chromium (VI) ⁿ	Lead (Pb)	Conclusion
CAS No.	7440-38-2	7440-43-9	18540-29-9	7439-92-1	
LOQ (mg/kg)	0.2	0.1	0.5	0.2	
Limit (mg/kg)	1	1	1	1	
Material No.	Result (mg/kg)				
1	N.D.	N.D.	N.D.	N.D.	PASS

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
 2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).
 3. The result of hexavalent chromium is expressed as the result of chromium. If the result of chromium is > 0.5mg/kg, the hexavalent chromium test shall be performed.


Test Result(s):

Polycyclic aromatic hydrocarbons - Annex XVII items 72 of the REACH Regulation (EC) No 1907/2006

Method: AfPS GS 2019:01 PAK, analyzed by Gas Chromatography-Mass Spectrometer (GC-MS) .

No.	Substances Name	CAS No.	Limit (mg/kg)	LOQ (mg/kg)	Result (mg/kg)
					1
1	Benzo(a)anthracene (BaA)	56-55-3	1	0.20	N.D.
2	Chrysene (CHR)	218-01-9	1	0.20	N.D.
3	Benzo(b)fluoranthene (BbF)	205-99-2	1	0.20	N.D.
4	Benzo(k)fluoranthene (BkF)	207-08-9	1	0.20	N.D.
5	Benzo(a)pyrene (BaP)	50-32-8	1	0.20	N.D.
6	Dibenzo(a,h)anthracene (DBA)	53-70-3	1	0.20	N.D.
7	Benzo(e)pyrene (BeP)	192-97-2	1	0.20	N.D.
8	Benzo(j)fluoranthene (BjF)	205-82-3	1	0.20	N.D.
Conclusion					PASS

- NOTE:**
1. mg/kg = milligram per kilogram (ppm).
 2. N.D. = Not Detected (Less than LOQ, LOQ = Limit of Quantitation).




Test Report

Report No.: CTT2409010211EN

Page 3 of 3

Test Material List

Material No.	Sample Description	Location
1	Black synthetic leather with dark blue fibre	Individual

Photo of Sample:***** End of Report *****

This test report is issued by the company subject to its General Conditions of Services and accessible at <http://www.cttlab.com/order/202103190908290166.pdf>. The sample and sample information are provided by the applicant, our company are not responsible for their integrity and authenticity. Unless otherwise stated the results shown in this report only apply to the sample as received. Any inquiry about this report, please raise from the date of receipt of the report within 30 days, overdue will not be accept. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" means they are not accredited by CNAS (if with CNAS logo), "s" means the item of subcontractor. This report is only used for scientific research, teaching, internal quality control, not for domestic social impartiality proof data.

